



A CSW Industrials Company

PRODUCT DATA SHEET

NOKORODE® HOT FLUX™
Hot Weather Paste Flux

Description

Nokorode Hot Flux is a lead free, soft soldering paste flux especially formulated to remain thick in hot weather applications. It is ideal for use with 95/5 and other common solders. It cleans and fluxes the joint area all at one time. When heated, it reduces the surface tension in the joint and allows the solder to flow easily and uniformly into the joint. Nokorode Hot Flux works to deliver a strong, leak-free joint. Its non-aggressive formula is ideal for use on copper and brass fittings.



Applications

Nokorode Hot Flux can be used with 95/5, 60/40, 50/50, and 40/60 solders. It can be used on all solderable metals including copper, tin, zinc, nickel, and sheet lead. Do not use on stainless steel, aluminum or magnesium. Not recommended for electronic use.

Directions for use

1. Remove all dirt from surfaces to be soldered.
2. Do not breathe vapors during soldering operations.
3. Apply a small amount of flux evenly to both joining surfaces. Heat and apply solder in normal manner.
4. When joint has cooled, wipe outside and flush inside surfaces thoroughly with water.
5. Flux paste may liquefy if stored under very hot conditions (usually greater than 125°F). Before using, cool slightly until flux re-solidifies.

For additional technical information, call Toll Free 1-800-231-3345.

Characteristics | Features

- Cleans and fluxes in one operation saving time and money
- Smooth consistency makes it easy to apply
- Flows smoothly into even the smallest cavity
- Lead free and acid free
- Multipurpose for use with 95/5, 60/40, 50/50, and 40/60 solder
- Low corrosivity,
- Low scorching
- Low spattering
- Meets: OF 506 Type 1 A & A-A-51145
- MIL-F-4995
- MIL-FS-6872A

Packaging

Code	Size	Qty. per Case	Lbs. per Case	Cubic Feet per Case
14820	8 oz. (227g)	24 jars	13.8	0.45
14830	16 oz. (454 g)	12 jars	14	0.45

NOKORODE® HOT FLUX™

Hot Weather Paste Flux

Specifications

Wt/Gal @ 77 degree F	~8.45 lbs/gal.
Flash Point SETA CC	>399°F
Color	Tan/gold to black paste
Shelf Life	2 year

Suggestions and recommendations covering the use of our products are based on our past experience and laboratory findings. However, as we have no control as to the methods and conditions of application, we only assume responsibility for the uniformity of our products within manufacturing tolerances.

Precautionary Statements

Refer to Safety Data Sheet (SDS).

KEEP OUT OF REACH OF CHILDREN

FOR CHEMICAL EMERGENCY, SPILL, LEAK, FIRE, EXPOSURE OR ACCIDENT, CALL CHEMTREC - DAY OR NIGHT 1-800-424-9300

For additional Technical Information Call Toll Free 1-800-231-3345

Limited Warranty



For more information on our product limited warranty, visit RectorSeal.com

Manufactured by

RectorSeal, LLC

2601 Spenwick Drive • Houston, TX 77055, USA • 800-231-3345 • Fax 800-441-0051 • rectorseal.com

A CSW Industrials Company. RectorSeal, the logos and other trademarks are property of RectorSeal, LLC, its affiliates or its licensors and are protected by copyright, trademark and other intellectual property laws, and may not be used without permission. RectorSeal reserves the right to change specifications without prior notice. ©2022 RectorSeal. All rights reserved. R50072-0522